

SC Color Paste

Pigment paste for epoxy system

FEATURES

Multicolor pigments premixed in an epoxy base.
Formulated to modify any epoxy system's color (paint, gelcoat, casted parts...)
The past consistency will ensure an easy mixing and color quality.
All RAL and AFNOR color grade available (except metallic colors)

PHYSICAL PROPERTIES

Aspect	Colored paste	
Color	According to RAL & AFNOR shades	
Viscosity (mPa.s) <i>Rheometer CP 50 mm gradient of shear 10 s⁻¹</i>	@ 25 ° C	20 000 to 150 000 mPa.s
Density : <i>Pycnometer ISO 2811-1</i>	@ 20 ° C	1,2 +/- 0,2
Storage stability:	12 months Must be homogenized before each use	

TIPS FOR USING

- Make sure the past is well mixed before using it.
- Incorporate the pigment paste into the resin or the resin/hardener mix with a good and slow stir.
- Recommended ratio: up to 15% per weight with the resin / hardener mix.
- Because the paste is premixed with an epoxy resin, it is possible to mix up to 10% per weight of the Color Paste into the resin only.
Above this limit, a new resin / hardener mixing ratio is needed. Thank you to contact us.
- Use in full shade, or gradation, it is possible to mix the different paste to get specific home made colors.

PRECAUTIONS

- Do not directly mix the color paste with hardener (only resin or mixed resin/hardener)
- The final color on filled resin can be different from the expected one.
- A preliminary test is required on a small amount of mixture to check compatibility, opacity, final color, etc...

PACKAGING

- Metal box 0.95 kg
- Metal bucket 20 kg

LEGAL NOTES: SICOMIN reserves the right to change the properties of its products. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data and tolerance may vary due to circumstances beyond our control. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

MENTIONS LÉGALES : SICOMIN se réserve le droit de modifier les propriétés du produit. Toutes les caractéristiques spécifiées dans cette Fiche technique sont basées sur des tests de laboratoire. Les mesures et leurs tolérances effectives peuvent varier pour différentes raisons. SICOMIN se réserve le droit Aucune garantie de quelque nature que ce soit, sauf que les matériaux fournis sont de qualité standard. Tous les risques et responsabilités découlant de la manutention, le stockage et l'utilisation des produits, ainsi que le respect des restrictions légales applicables, incombe à l'utilisateur.