

CIREX Si 111 Release Agent

SHAKE THOROUGHLY BEFORE USE

Description

Cirex Si 111 is a soft paste external release agent. It evaporates at room temperature and forms a film which sticks to the mould surface instead of the resin. It is silicon free.

It acts as an anti corrosion protection on the metallic moulds while avoiding any special preparations for a long storage time

Advantages

- **Cirex Si 111** has been created for polyester and epoxy resins and also for the PU resins (elastomer and foam). It has been specially formulated to obtain a thin coat of wax which can be easily applied on the moulds, the borders and the technical areas, while avoiding contamination of the mould.
- There is no risk of fish eyes

Application

1. During the 1st treatment, apply 3-4 coats of **Cirex Si 111** with a brush, or a cloth. Leave 15mn between each coat minimum (at 20°C). Then buff it after in order to get rid of the excess.
2. Mould after a minimum of one hour

NOTE: in case of a PU (RIM, foams and elastomer) mould, a slight coat is needed before each mould

Physical properties

- Max temperature 130°C
- Life span 1 year, in closed container

Packaging

5 liters / 3,95 kg

LEGAL NOTES: SICOMIN reserves the right to change the properties of its products. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data and tolerance may vary due to circumstances beyond our control. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

MENTIONS LÉGALES : SICOMIN se réserve le droit de modifier les propriétés du produit. Toutes les caractéristiques spécifiées dans cette Fiche technique sont basées sur des tests de laboratoire. Les mesures et leurs tolérances effectives peuvent varier pour différentes raisons. SICOMIN ne donne aucune garantie de quelque nature que ce soit si ce n'est que les matériaux fournis sont de qualité standard. Tous les risques et responsabilités découlant de la manutention, le stockage et l'utilisation des produits, ainsi que le respect des restrictions légales applicables, incombe à l'utilisateur.